

SPINNING YARN QUALITY CRITERION

CVC32/1

Yarn count (Ne)	: 32/1
Yarn composition	: 60/40

FINENESS :

$CV_{Ne} \%$: 1.5
$\Delta_{Ne} \%$: ± 1.0

YARN TWIST :

Yarn twist (T.P.M)	: 813
CV twist ($CV_k \%$)	: 3.5
Δ twist ($(\Delta_k \%)$)	: ± 2

YARN STRENGTH :

Absolute strength P (cN)	: 350
Relative strength Po (cN / Tex)	: 18.98
CV strength ($CV_P \%$)	: 77
Breaking elongation (E %)	: 7.5

UNEVENNESS :

Uster unevenness (U%)	: 10.2
CV uster unevenness ($CV_m \%$)	: 12.8
Thins / km (-50%)	: 5
Thicks / km (+50%)	: 30
Neps / km (+200%)	: 65
Hairiness (H %)	: 6