

SPINNING YARN QUALITY CRITERION

TC60/1

Yarn count (Ne)	: 60/1
Yarn composition	: 65/35

FINENESS :

$CV_{Ne} \%$: 1.5
$\Delta_{Ne} \%$: ± 1.0

YARN TWIST :

Yarn twist (T.P.M)	: 1073
CV twist ($CV_k \%$)	: 3.5
Δ twist ($(\Delta_k \%)$)	: ± 2

YARN STRENGTH :

Absolute strength P (cN)	: 190
Relative strength Po (cN / Tex)	: 19.33
CV strength ($CV_P \%$)	: 11
Breaking elongation (E %)	: 8.7

UNEVENNESS :

Uster unevenness (U%)	: 12.5
CV uster unevenness ($CV_m \%$)	: 15.6
Thins / km (-50%)	: 40
Thicks / km (+50%)	: 170
Neps / km (+200%)	: 220
Hairiness (H %)	: 4